



Technical Information

Product name	:	MoTip Hammerfinish lacquer					
Colour	:	Blue	Green	Silver	Grey	Gold	Antracite
Article number	:	04011	04012	04013	04014	04015	04017
Supplier / Producer	:	MOTIP DUPLI B.V. Wolframweg 2 NL-8471 XC WOLVEGA					
		Telephone number			+31 561 – 69 44 00		
		Telefax number			+31 561 – 69 44 31		

Product description

High quality lacquer with hammered effect to treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic.

Product characteristics

Fast drying
Good coverage
Scratch free and shock proof
Resistant to petrol, chemicals, thinned cleaners and weather influences

Physical and Chemical Characteristics

Contents	:	400 ml
Base	:	Alkyd resin
VOC-content	:	Approximately 82% w/w
Solid content	:	Approximately 18% w/w
Coverage	:	1,25 to 1,75 m ²
Dust dry	:	After 5 to 10 minutes
Tack free	:	After 10 to 20 minutes
Hardened/re-sprayable	:	After 24 hours
Heat resistant	:	To 110°C

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of MoTip primer suitable for the surface. After drying, sand the base layer (grain 600).

Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply a thin first layer and after several minutes apply a finishing coat. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.